


## Proeftesten Coolrec

Kenmerk :

Machine No. : X350-3108  
 Test Name : Coolrec trekproef  
 Test Type : Tensile  
 Test Date : 11-10-2021 13:06  
 Test Speed : 20,000 mm/min  
 Speed 2 : 50,000 mm/min  
 Point : 8,000 mm  
 Pretension : 10,000 N  
 Width : 10,000 mm  
 Thickness : 4,000 mm  
 Extensometer : Epsilom 50mm  
 Gauge Length : 50,000 mm  
 Sample Length : 100,000 mm

Test No	Youngs Modulus (N/mm <sup>2</sup> )	Force @ Peak (N)	Stress @ Peak (N/mm <sup>2</sup> )	Strain @ Peak (%)	Stress @ Break (N/mm <sup>2</sup> )	Strain @ Break (%)	Stress @ Break (V2) (N/mm <sup>2</sup> )
1	1862,83	753,3	18,833	32,874	11,98	33,632	11,98
2	1811,186	715,6	17,89	21,719	15,95	22,52	15,95
3	1850,753	763,3	19,083	31,175	13,753	31,563	13,753
Mean	1841,59	744,067	18,602	28,589	13,894	29,238	13,894
S.D.	27,013	25,155	0,629	6,01	1,989	5,909	1,989



— Test 1 — Test 2 — Test 3